





NOTES:

1. MATERAIL: SYNTHETIC QUARTZ
2. COATING (S1) : MULTI-LAYER DIELECTRIC COATING
 $R > 98\% @ 257 \text{ nm}, 45^\circ \pm 3^\circ \text{ AOI}$
3. CLEAR APERTURE (S1) : $> 90\%$ (CA)
4. SURFACE QUALITY (S1) : 10/5 (S/D)
5. SURFACE FLATNESS (S1) : $\lambda/10 @ 633 \text{ nm}$
6. PARALLELISM (S1,S2) : $< 3'$
7. CHAMFER: $0.5 \pm 0.1 \times 45^\circ$
8. BACK SURFACE (S2) : FINE GROUND

MULTI-LAYER DIELECTRIC-COATED
PLATE MIRROR

MLOPTIC | 茂莱

OP-M-HP-25.4C05-10/5-257

ISSUE	SCALE	PAGE	FIRST ANGLE
A0	1:1	1 OF 1	