





#### NOTES:

1. MATERAIL: SYNTHETIC QUARTZ
2. COATING (S1) : MULTI-LAYER DIELECTRIC COATING  
 $R > 99\% @ 1030 \text{ nm}, 45^\circ \pm 3^\circ \text{ AOI}$
3. CLEAR APERTURE (S1) :  $> 90\%$  (CA)
4. SURFACE QUALITY (S1) : 10/5 (S/D)
5. SURFACE FLATNESS (S1) :  $\lambda/10 @ 633 \text{ nm}$
6. PARALLELISM (S1,S2) :  $< 3'$
7. CHAMFER:  $0.5 \pm 0.1 \times 45^\circ$
8. BACK SURFACE (S2) : FINE GROUND

MULTI-LAYER DIELECTRIC-COATED  
PLATE MIRROR

MLOPTIC | 茂莱

OP-M-HP-12.7C03-10/5-1030

| ISSUE | SCALE | PAGE   | FIRST ANGLE |
|-------|-------|--------|-------------|
| A0    | 1:1   | 1 OF 1 |             |